

Microleakage evaluation of Standard and Expired Composites and bonding agents at the dentin-resin interface: An in vitro study¹Dr. Mustafa Hajoori, Karnavati University, Gandhinagar**Corresponding Author:** Dr. Mustafa Hajoori, Karnavati University, Gandhinagar**How to citation this article:** Dr. Mustafa Hajoori, “Microleakage evaluation of Standard and Expired Composites and bonding agents at the dentin-resin interface: An in vitro study”, IJMACR- December - 2023, Volume – 6, Issue - 6, P. No. 25 – 30.**Open Access Article:** © 2023, Dr. Mustafa Hajoori, et al. This is an open access journal and article distributed under the terms of the creative common’s attribution license (<http://creativecommons.org/licenses/by/4.0>). Which allows others to remix, tweak, and build upon the work non-commercially, as long as appropriate credit is given and the new creations are licensed under the identical terms.**Type of Publication:** Original Research Article**Conflicts of Interest:** Nil**Abstract****Introduction:** For a restoration to be successful, one of the key properties of the material is to prevent microleakage. Even though shelf life of composite resin and bonding agent in an important factor, they can be used for simple procedures even after their expiration date. The aim of the study was to determine the effect on microleakage of standard and one-year expired composites and bonding agents.**Materials and methods:** Selected forty specimens were etched for 15 seconds in 37 percent phosphoric acid and randomly divided into four groups: Non-Expired composite and bonding agent; Expired composite and bonding agents; non-expired composite and expired bonding agent; Expired composite and non-expired bonding agent; and Expired composite and non-expired bonding agent. Using a stereomicroscope, specimens were sectioned longitudinally and examined for leakage (dye penetration).**Results:** The results of the present study indicated significant differences in microleakage scores between group 1 and group 2. Mann-Whitney U test showed that all the four groups are statistically non-significant so there is no statistically significant difference between any two groups.**Conclusion:** These findings of the study indicated that expired composites and bonding agents showed acceptable values in terms of microleakage.**Keywords:** Expired composite resin, Microleakage, Expired bonding agent, Dentistry**Introduction**Essentially polymeric materials, restorative composites work better in vitro and in vivo depending on the chemical structural configuration, the rate of deterioration over time, and other factors.^[1] The deterioration of resin composites is a multifaceted, complex process. Two main types of degradation can be seen: extraoral deterioration brought on by the storage of the substance and its shelf life, and intraoral degradation (mechanical, physical, or

chemical). Many of the materials used in dentistry must be stored in a certain way to preserve their optimal characteristics and lengthen their shelf life.

A mixture of impacts from oxidative chain scission, oxidation hydrolysis, changes in crystallinity, and other variables that may be reliant on the environmental storage may result in the degradation, which may be mostly chemical in nature.^[2]

The batch number, the expiration date, and the storage instructions are printed on the box of each syringe of composite that a dentist purchases. The shelf life of the majority of direct composite restoratives is short. The shelf life of a material is defined by the American National Standards Institute (ANSI) as the amount of time (counting from the date of manufacturing) during which a material maintains the physical and mechanical attributes required to fulfill its intended purpose.^[3]

Between uses, dental supplies are stored on a shelf or in the refrigerator for extended periods of time. The components of the material must thus not separate, evaporate, react, or degrade during this time when it is no longer in use.^[4]

Materials made of resin need to be stored carefully to keep their full efficiency.

Typically, a temperature range of 4°C and 20°C is advised. However, because resin composite storage requirements might vary depending on the geographic and climatic parameters (sun exposure and humidity) of the country, the majority of dental manufacturers advise refrigerated resin composite storage.

When not in use, chemically- and dual-cured composites should be kept in the refrigerator, and they should be given at least one hour to acclimate to room temperature. When stored in a cold environment, the auto cured component of dual composites has a shelf life of around

18 to 24 months. However, these composites have a reduced lifespan when stored at room temperature. Contrarily, light-cured composites have a predicted shelf life of roughly 5 years since they are stable at room temperature if kept sealed to prevent monomer evaporation.^[5]

Investigated was the impact of unsupervised outdoor storage in a variety of environments. Chemically-cured composites appear to be more susceptible to the effects of storage than light-cured composites.^{[6],[7]} The storage stability of restorative dental biomaterials has been the subject of several investigations that have been published.^{[8],[9],[10],[11],[12],[13]}

One crucial aspect to take into account is the resin composite's expiration date. The material qualities might theoretically change if utilised past the given expiration date. Clinically speaking, this could result in failures such fracture, excessive wear, and discolouration. Dentists can use some resin composites past the manufacturer's indicated expiration date in their routine care. Should they throw away those materials or can they use them for a brief time?

Null hypothesis

The study is conducted with a null hypothesis stating that microleakage seen in one-year expired composite and bonding agent would be significantly higher than that seen in non-expired composite and bonding agent.

Materials and method

This study was conducted in the Department of Conservative Dentistry and Endodontics, after obtaining Institutional Ethical Committee Approval (KSDEC/21-22 June/080). Forty, recently extracted human permanent molars, which were extracted for periodontal reasons were included. The exclusion criteria were: presence of any caries, old restorations, cracks, or hypoplastic defects.

The teeth were then cleaned with ultrasonic instruments. They were then classified into four categories based on the composite and bonding agent used:

Group 1: Non-Expired composite and non-expired bonding agent

Group 2: One-year Expired composite and Expired bonding agent

Group 3: Non-Expired composite and one-year expired bonding agent

Group 4: One-year Expired composite and non-expired bonding agent.

Cavity Preparation: Class I cavities were prepared by using straight fissure bur GW557, SS White, New Jersey), with a high-speed handpiece. The dimensions of the cavity were kept as follows length: 3 mm, width: 2 mm and depth: 3 mm. Copious amount of water was used as a coolant. The cavities were then rinsed with a water spray. Dentin of the prepared cavity wall was etched with 37 percent phosphoric acid for 15 seconds. The etching gel was then sprayed away with water for 10 seconds. The bonding agent (Ivoclar Vivadent, USA) was applied per the manufacturer's instructions. The cavity was then filled with composite Tetric N Ceram A2 (Ivoclar Vivadent, USA) in 2 increments and cured after placing each increment. The restoration was finished and polished using polishing discs.

Oral conditions were simulated by placing the specimens in distilled water bath at 37°C for 24 hours followed by thermocycling them for 500 cycles between water baths held at 5°C and 55°C with a 30-second dwell time in each bath with a transfer time of 2 seconds.

The teeth were then dried and sealed with nail varnish. The varnish was kept 1 mm short of the restoration margins. The varnish coated teeth were then immersed in a 2% methylene blue solution for 24 hours.

The samples were then removed from the die were washed with water. They were then sectioned through the center of the restorations in a Bucco-lingual direction using a slow-speed straight hand piece and D+Z diamond disc. Finally, using a stereomicroscope, they were visually examined for dye penetration along cavity walls. (Olympus at a magnification of $\times 40$).

For measurement of microleakage, a scoring system was used as^[14]:

0—no dye penetration;

1—dye penetration into half extension of the cavity wall;

2—dye penetration into more than half or complete extension of the cavity wall;

3—dye penetration into the pulpal floor.

Results

Figures 1 to 4 show the microleakage exhibited by the samples as seen in the stereomicroscope (40X) along with the scoring criteria. Table 1 shows the mean value \pm standard deviation of microleakage scores for all the groups with maximum microleakage for one-year expired composite and expired bonding agent and minimum microleakage for non-expired composite and non-expired bonding agent. Kruskal-Wallis's test indicates statistically non-significant values of microleakage among all the groups with a p-value of 0.630.

The results of the microscopic examination revealed no marked difference in dye penetration between the groups. For intergroup comparison, Mann-Whitney U test was applied which shows that all the four groups are statistically non-significant so there is no significant difference between any two groups.

Thus, this study evaluated that the degree of microleakage in descending score is as follows:

Group II (mean score of microleakage 1.6) > Group IV (mean score of microleakage 1.4) > Group III (mean score

of microleakage 1.3) > Group I (mean score of microleakage 1.1)

Discussion

Composites have been widely used in recent decades due to their aesthetic qualities. However, related issues, such as microleakage and postoperative sensitivity, persist and cause doctors to be confused about its application in a variety of situations. All of these problems are said to be linked to traditional composites. As a result, it is reasonable to assume that using one-year expired composites will worsen these qualities even further. Despite of composites being expired, the higher cost of this material forces dentists to use it despite the risks. The attributes of expired composites and bonding agents were therefore studied and compared with those of the standard composite in various combinations, with an emphasis on the amount of usage of expired composites, taking into consideration the great popularity of this extravagant material. [3]

Microleakage can be assessed using various techniques, die penetration being the most commonly used as it is inexpensive and easy to use. Various dyes such as methylene blue, basic fuchsin, erythrosine can be used to study microleakage. The most commonly used organic dye is Methylene blue in the concentration ranging from 0.5% to 5% as it is easily available, easy to handle, inexpensive and has a high degree of staining. [15]

On intergroup comparison, the microleakage scores were significant between the normal and the one-year expired composites and bonding agents. All the four groups are statistically non-significant so there is no statistically significant difference between any two groups. The shift in microleakage of expired composite might be explained by partial polymer cure, which could be caused by the

breakdown of the components involved in the polymerization of this material over time. [16]

Söderholm KJ et al. [17] discovered that ion leakage into the uncured monomer causes a reduction in the filler particles of restorative composites held in liquid medium for particular durations of time. This is regulated by the photo initiator concentration, which declines throughout the material's shelf life. For example, if the silane coupling agent has deteriorated, a composite may wear out faster than intended. [18]

There are numerous and diverse methods by which composite resins can deteriorate in the oral cavity, which are now recognized as a complex interplay of interactions. [19]

- There is rising concern about the safe clinical usage of these materials due to their biodegradation in the oral environment.
- Biodegradation is caused by a variety of factors, including saliva characteristics, chewing, thermal, and chemical dietary changes.

According to Humdrums' findings, a visible light-cured composite may preserve particular physical features for up to 7 years. Although it is not recommended to use expired dental materials, the qualities of the material altered by ageing are yet unclear. Although we advocate for extending the shelf life of these pricey materials, the extent to which they may be utilized effectively after their expiry date should be established by more study, as well as the evaluation of other desired features. [6]

Another study done by Ferracane JL. failed to report any notable changes in the hardness and water sorption of six month old composite when compared with standard composite. [19]

Conclusion

Current findings of the study indicated that expired composites and bonding agents showed acceptable values in terms of microleakage. Despite the fact that composite has the best properties when it is not expired, expired composite Tetric N Ceram (Ivoclar Vivadent) with standard Tetric N Bond (Ivoclar Vivadent) agent can be used in clinical situations when availability is questionable.

Clinical Significance of the study

The expiration date of a resin composite is an important consideration. Material qualities may be affected if utilized after the specified expiration date. Clinically, this may result in failures such as fracture, excessive wear, and discoloration. When not in use, chemically and dual-cured composites should be refrigerated and allowed to come to room temperature for at least 1 hour before use. For a better understanding of the effect of the expiration date on resin-based materials, other properties with clinical implications such as working duration, consistency, and effect of ambient light should be explored.

Limitations of the study

Mechanical loading, salivary characteristics were not undertaken in this study as different findings may have been found if the restorations had experienced occlusal stresses from masticatory loading. Another disadvantage of this study was that specimens were only evaluated using a stereomicroscope.

References

1. Drummond JL. Degradation, fatigue, and failure of resin dental composite materials. *Journal of dental research*. 2008 Aug;87(8):710-9.
2. Sabbagh J, Nabbout F, Jabbour E, Leloup G. The effect of expiration date on mechanical properties of

resin composites. *Journal of International Society of Preventive & Community Dentistry*. 2018 Mar;8(2):99.

3. Talreja N, Singla S, Shashikiran ND. Comparative Evaluation of Bond Strength and Microleakage of Standard and Expired Composite at Resin-Dentin Interface: An in vitro Study. *International Journal of Clinical Pediatric Dentistry*. 2019 Jan;10(1):1.
4. D'Alpino PH, Svizero Nda R, Arrais CA, de Oliveira M, Alonso RC, Graeff CF, et al. Polymerization kinetics and polymerization stress in resin composites after accelerated aging as a function of the expiration date. *J Mech Behav Biomed Mater*. 2015; 49:300–9.
5. Fallo GJ, Wakefield CW, Czerw RJ. Effects of uncontrolled outdoor storage on the polymerization, manipulation, and appearance of visible light-cured composite resin and resin-modified glass ionomer materials. *Military medicine*. 1996 May 1;161(5):290-3.
6. Hondrum SO, Fernandez Jr R. The storage stability of dental composite resins: seven-year results. *General Dentistry*. 1997 Jul 1;45(4):382-9
7. Oja J, Lassila L, Vallittu PK, Garoushi S. Effect of accelerated aging on some mechanical properties and wear of different commercial dental resin composites. *Materials*. 2021 Jan;14(11):2769.
8. Mondal D, Willett TL. Mechanical properties of nanocomposite biomaterials improved by extrusion during direct ink writing. *Journal of the Mechanical Behavior of Biomedical Materials*. 2020 Apr 1; 104:103653.
9. Rohr N, Fischer J. Effect of aging and curing mode on the compressive and indirect tensile strength of resin composite cements. *Head & face medicine*. 2017 Dec;13(1):1-9.

10. Szczesio-Wlodarczyk A, Fronczek M, Ranoszek-Soliwoda K, Grobelny J, Sokolowski J, Bociong K. The First Step in Standardizing an Artificial Aging Protocol for Dental Composites—Evaluation of Basic Protocols. *Molecules*. 2022 May 30;27(11):3511.
11. Liebermann A, Roos M, Stawarczyk B. The effect of different storage media on color stability of self-adhesive composite resin cements for up to one year. *Materials*. 2017 Mar 16;10(3):300.
12. Iliev G, Hardan L, Kassis C, Bourgi R, Cuevas-Suárez CE, Lukomska-Szymanska M, Mancino D, Haikel Y, Kharouf N. Shelf life and storage conditions of universal adhesives: A literature review. *Polymers*. 2021 Aug 13;13(16):2708.
13. Frigione M, Rodríguez-Prieto A. Can Accelerated Aging Procedures Predict the Long-Term Behavior of Polymers Exposed to Different Environments? *Polymers*. 2021 Aug 12;13(16):2688.
14. Nagaoka H, Bishop S, Roberts H. Flexural performance of direct resin composite restorative materials past expiration date. *European Journal of Dentistry*. 2020 May;14(02):217-23..
15. Nassaj AE, Ghadimi S, Seraj B, Chiniforush N. Effect of photodynamic therapy on microleakage of class V composite restorations in primary teeth. *Photodiagnosis and Photodynamic Therapy*. 2020 Dec 1;32:101964.
16. Kalyana Krishnan V, Yamuna V. Effect of initiator concentration, exposure time and particle size of the filler upon the mechanical properties of light-curing radiopaque dental composite. *J Oral Rehabil* 1998 Oct;25(10):747-751
17. Söderholm KJ, Zigan M, Ragan M, Fischlschweiger W, Bergman M. Hydrolytic degradation of dental composites. *J Dent Res* 1984 Oct;63(10):1248-1254.
18. Lopes-Rocha L, Ribeiro-Gonçalves L, Henriques B, Özcan M, Tiritan ME, Souza JC. An integrative review on the toxicity of Bisphenol A (BPA) released from resin composites used in dentistry. *Journal of Biomedical Materials Research Part B: Applied Biomaterials*. 2021 Nov;109(11):1942-52.
19. Ferracane JL. Models of caries formation around dental composite restorations. *Journal of dental research*. 2019 Apr;96(4):364-71.